



## ANALYSIS CERTIFICATE

25 July, 2022

OUR REF:	107772A
TO:	Ardex NZ Ltd
ATTN:	Steven Irvine

SAMPLE OF:	Ardex P51	SAMPLE TYPE:	As received
SAMPLE TYPE:	Primer and Bonding Agent	DATE RECEIVED:	18/07/2022
SAMPLE DATE:	-	DATE TESTED:	18-20/07/2022
		ORDER NO:	-


SPECIFICATION:	Green Building Council of Australia Green Star Design & As Built V1.3-13.1.1B Green Star Interiors V1.3-12.1.1B
DETAILS:	Max TVOC content in grams per litre (g/L) of ready to use product in the category of 'Primers, sealers, and prep coats' = 65

### RESULTS

	Result	Method
Total Non-Volatile Content, %w/w	40.8	Oven-drying @ 110°C (60mins)
Total Water Content, %w/w	54	Karl Fischer titration
Density, g/mL	1.03	Gravimetry
Exempt Compounds	None specified	

	Result	Method
Total Volatile Organic Compounds, g/L	54	SCAQMD METHOD 304-91

**Note:** Specification was provided by the client. This sample complies with the specification.

Analyst 

Authorised by 

This report relates only to the sample provided

**This Report Shall Not Be Reproduced Except In Full**

**MEMBER OF THE NEW ZEALAND ASSOCIATION OF CONSULTING LABORATORIES**

37 Spring Street, Freemans Bay, Auckland 1011 - PO Box 437, Shortland Street, Auckland 1140, New Zealand

Phone: (09) 360 2077 - Mobile: 021 145 1567 - Email: office@flinderscook.co.nz

Website: www.flinderscook.co.nz