



ARDEX WPM 115

Shelterbit Vented Base Sheet

0.8mm APP Bitumen Vented Base Sheet

DISCLAIMER The technical details, recommendations and other information contained in this data sheet are given in good faith and represent the best of our knowledge and experience at the time of printing. It is your responsibility to ensure that our products are used and handled correctly and in accordance with any applicable New Zealand Standard, our instructions and recommendations and only for the uses they are intended. We also reserve the right to update information without prior notice to you to reflect our ongoing research and development program. Country specific recommendations, depending on local standards, codes of practice, building regulations or industry guidelines, may effect specific installation recommendations. The supply of our products and services is also subject to certain terms, warranties and exclusions, which may have already been disclosed to you in prior dealings or are otherwise available to you on request. You should make yourself familiar with them.

ARDEX WPM 115

Shelterbit Vented Base Sheet

0.8mm APP Bitumen Vented Base Sheet



PRODUCT DESCRIPTION

Ardex WPM 115 (Shelterbit Vented Base Sheet) is an APP (Atactic Polypropylene) plastomeric type modified bitumen membrane vented base sheet, consisting of a specially formulated bituminous compound of distilled asphalt modified with selected high grade visco-elastic polymers.

A protective heat sensitive polythene film covers both surfaces of the Base Sheet.

FEATURES/BENEFITS

- Is a specially designed perforated base-sheet for use in a multi-layer waterproofing system.
- Virtually eliminates bubbles and blisters forming underneath the waterproofing layer.
- Allows vapour permeating through the deck to diffuse underneath the waterproofing where, ideally, aerators will be installed to allow the vapour to escape to atmosphere.
- Eliminates the creation of stresses in the waterproofing layers thus greatly reducing failures in the waterproofing caused by deck movements.
- Is the ideal solution for controlled, partially attached first layer in a multi-layer system.

INSTALLATION

The application of Ardex Shelterbit should be carried out by an approved Applicator.

Concrete

After priming of substrate Ardex WPM 115 (Shelterbit Vented Base Sheet) may be loose laid or may be tacked in place to locate sheet until next layer is installed.

Installation shall be strictly in accordance with the manufacturer's recommendations.

Acceptable substrates to which Ardex Shelterbit is to be installed must be properly prepared prior to membrane installation.

Ardex Shelterbit may be used in various combinations to produce a variety of specifications tailored to suit the individual waterproofing need.

The exact specification will depend on functional and economic requirements. Advice should be sought for suitable specification from Ardex.

SAFETY PRECAUTIONS

Ardex Shelterbit is not classified as dangerous goods. However during installation exercise caution when working with open flame. Examine all surfaces to which the flame has been applied for smouldering or burning conditions.

Do not use open flame on or near highly combustible materials. Follow all local fire codes.

STORAGE

All rolls of Ardex Shelterbit should be stored in a covered area protected against sunlight and UV radiation. Rolls should be stored in a vertical position on a smooth floor so as not to damage the edges.

PACKAGING

Roll size: 1m x 20m

Roll weight: Approximately 20kg

Rolls per pallet: 33

TECHNICAL DATA

The Technical Data shown here below are the average results of the Tests, Measurements and Trials, carried out on Ardex WPM 115 (Shelterbit Vented Base Sheet).

Characteristics	Standard	Units	Nom.
Length	UNI EN 1848-1	m	20
Width	UNI EN 1848-1	m	1.0
Thickness	UNI EN 1849-1	mm	0.8
Hole Diameter		mm	40
Number of Holes		per m ²	119
Heat Stability	UNI EN 1110	°C	110
Cold Flexibility	UNI EN 1109	°C	-5
Tensile strength	UNI EN 12311-1		
Ultimate Longitudinal	N/5	cm	310
Ultimate Transverse	N/5	cm	205
Elongation at Break	UNI EN 12311-1		
Longitudinal		%	2
Transverse		%	2
Tear resistance	UNI EN 12310-1		
Longitudinal		N	70
Transverse		N	80
Reinforcement	Glass Fibre	g.s.m.	60
Surface finishes	Lower ¹	torch film	
	Top ²	torch film	

Note 1) Lower surface; the surface which is applied to the structure being waterproofed.

Note 2) Top surface; exposed to underside of covering membrane.

All tests have been carried out to UEATC, to tolerances as per European Directive.