



ARDEX HYDROSTOP WPM 1950

Polymeric Hydrophilic Rubber Joints

Non-greasy , non-sticky, odourless and non-toxic

Excellent for applications to rough concrete surfaces

No premature expansion; allows concrete to gain strength before expansion

Easy to install by bonding, nailing or casting into joint faces with the aid of ARDEX CA20P

Solves detailing problems in construction

Excellent performance - Swelling properties unaffected by long term cyclic wetting and drying; limited loss of integrity of waterstop.

Sustains effective seal in wet conditions.

ARDEX Australia Pty Ltd

20 Powers Road
Seven Hills NSW 2147
Phone: 1300 788 780
Email: techinfo@ardexaustralia.com
www.ardexaustralia.com

ARDEX New Zealand Ltd

15 Alfred Street
Onehunga, New Zealand
0800 227 339
info@ardexnz.com
www.ardex.co.nz

ARDEX HYDROSTOP WPM 1950

Polymeric Hydrophilic Rubber Joints

PRODUCT DESCRIPTION

Due to its particular chemical composition, ARDEX Hydrostop WPM 1950 hydrophilic rubber joint remains unaltered over time even at maximum expansion. It is dimensionally stable even after numerous hydration and dehydration cycles while maintaining its ability to increase its volume.

In its maximum expansion, in all its sections, ARDEX Hydrostop WPM 1950 hydrophilic rubber joint is mechanically strong and elastic. The swelling process is controlled and designed to be compatible with fresh concrete.

COMPOSITION

ARDEX WPM 1950 is made up of butyl rubber and aggregated polypropylene with high cohesion polymeric binders. These hydrophilic components activate in wet conditions which allows the Hydrostop to increase in volume.

APPLICATION INSTRUCTIONS

NOTE: A LBP is required to carry out Restricted Building Work. A LBP must do or supervise this work. They must work within the scope of their licence class.

ARDEX Hydrostop WPM 1950 Hydrophilic rubber joint must be applied to the support with nails or cement adhesives to remain attached to the in the early stages of concrete casting. For maximum performance ARDEX Hydrostop WPM 1950 hydrophilic rubber joint should be placed between the reinforcing bars or in a support with raised edge of at least 8/10cm. The joints are realized by matching sideways the rubber strip for at least 5cm, while avoiding overlapping.

Technical Data

Specific weight	ISO 1183	1.26kg/dm ³
Operating temperature	ISO 458/2	about +4°C
Max. expansion		350%
Hardness	ISO 868	60 shore A
Load at break	ISO 527	25 N/mm ²
Elongation at break	ISO 527	300%
Durability		unlimited
Sections	Various	

DISCLAIMER

The technical details, recommendations and other information contained in this data sheet are given in good faith and represent the best of our knowledge and experience at the time of printing. It is your responsibility to ensure that our products are used and handled correctly and in accordance with any applicable New Zealand & Australian Standards, our instructions and recommendations and only for the uses they are intended. We also reserve the right to update information without prior notice to you to reflect our ongoing research and development program. Country specific recommendations, depending on local standards, codes of practice, building regulations or industry guidelines, may effect specific installation recommendations. The supply of our products and services is also subject to certain terms, warranties and exclusions, which may have already been disclosed to you in prior dealings or are otherwise available to you on request. You should make yourself familiar with them. © ARDEX New Zealand Ltd 2016. All aforementioned products are the trade marks of ARDEX New Zealand Ltd.

The application surface should be clean, compact, properly vibrated and free of any irregularities.

BENEFITS

ARDEX Hydrostop WPM 1950 hydrophilic rubber joint is non-greasy, non-sticky, odourless and non-toxic. Due to its ductility it can be used in all conditions. Once the Hydrostop is secured into place no additional bonding is required and it will maintaining its seal in vertical laying as well as wet conditions.

PACKAGING

ARDEX Hydrostop WPM 1950 hydrophilic rubber joint is packed in cartons with 6 rolls of 8mt long coils giving a total of 48 linea meters per carton. Profiles and sizes are those normally used on the construction site; profiles with particular sections are available on request.

Dimensions:

WPM 1950 20mm x 10mm x 8mt roll

6 rolls per carton equals 48 linea meters per box.

LIMITATIONS

In cases of uncertainty regarding the salt content of the water, preliminary tests need to be done. For further information please contact ARDEX technical services.