



---

# ARDEX WPM 750

## Internal Weldable Undertile Sheet Membrane

---

Manufactured in New Zealand

BRANZ Appraised (No. 727)

Heat-welded laps and seams

Fleece-lined for greater adhesion

Begin tiling after 60 minutes

Thin and consistent membrane thickness

Suitable for use with underfloor heating systems

Excellent flexibility - no requirement for fillet or bond breakers

Excellent resistance to tearing, cracking, bubbling, and absorption

Fully compatible with ARDEX tiling systems

**WeldTec**<sup>™</sup>



**BRANZ Appraised**  
Appraisal No. 727 [2017]

---

**ARDEX New Zealand Ltd**  
15 Alfred Street  
Onehunga, Auckland 1061  
Phone: 0800 227 339  
Email: [info@ardexnz.com](mailto:info@ardexnz.com)  
**ardex.co.nz**

# ARDEX WPM 750

## Internal Weldable Undertile Sheet Membrane

### DESCRIPTION

ARDEX WPM 750 is a fleece-lined waterproofing sheet membrane specially formulated for the direct adhesion of tiled surfaces. ARDEX WPM 750 is heat-welded at laps and seams to create a superior bond, consistent gauge and allow a quick installation. ARDEX WPM 750 has excellent flexibility, durability, and superior resistance to tearing, cracking, bubbling and absorption.

### USES

ARDEX WPM 750 is specifically designed to be used as an internal waterproofing membrane for directly adhered tiled surfaces. ARDEX WPM 750 is suitable for use with most ARDEX tile adhesives in domestic and commercial locations over most common substrates.

### SUBSTRATES

Suitable substrates include concrete, plywood, CFC sheet, timber, closed cell polyurethane foam, paper-faced plasterboard.

For further substrate types please consult ARDEX Technical Department.

### SURFACE PREPARATION

The surface being adhered to must be clean, firm and free dust, dirt, oil, grease, curing compounds, release agents and other barrier materials that may damage the membrane.

### PRIMING

Prior to the application of ARDEX WPM 750 in cases of extreme porosity the surface may require priming with a suitable ARDEX primer in accordance with the product datasheet. Coverage of primer may depend on the porosity of the substrate.

The exact specification will depend on functional and economic requirements. Advice should be sought for suitable specification from ARDEX.

### INSTALLATION

The installation of ARDEX WPM 750 should be carried out by an approved ARDEX Installer.

Installation shall be undertaken in accordance with all relevant technical information related to the selected installation method, including information contained within the ARDEX installation documents.

ARDEX WPM 750 is to be adhered with a suitable adhesive such as ARDEX AF 620 or ARDEX WA 88 in accordance with the appropriate product datasheet.

ARDEX ST Tapes should be used for detailing or reinforcement of critical areas.

### HEATING

ARDEX WPM 750 is suitable for use with underfloor heating systems. For electric underfloor heating systems, ensure that wires are encapsulated with an appropriate ARDEX screed/levelling compound such as ARDITEX NA. For further recommendations contact ARDEX.

### STORAGE

ARDEX WPM 750 has an indefinite shelf life when stored in good conditions, between 5°C and 30°C. Store rolls horizontally in dry conditions out of direct sunlight. Store away from sources of puncture and physical damage. Store away from ignition sources and open flame.

### PACKAGING

ARDEX WPM 750 comes in rolls of 1.4m x 20m x 0.75mm. Each roll covers 28m<sup>2</sup>.

### PRECAUTIONS

ARDEX WPM 750 is considered non-hazardous in normal use, however good hygiene practices should be followed. Consult the relevant Safety Data Sheets for further information.

ARDEX WPM 750 is not suitable as a trafficable surface nor as an exposed membrane. If ARDEX WPM 750 is needed to be left exposed before tiling commences, ensure that care is taken to protect from general traffic and any source of damage.

### TECHNICAL DATA

Characteristics	Test Method	Nominal Value
Gauge		0.75mm
Specific gravity	ASTM D297	1.26 ± 0.05
Tensile strength	ASTM D412	5.0 MPa min.
Modulus at 300% elongation	ASTM D412	4.00 MPa min.
Elongation at break	ASTM D412	300% min.
Tear die	ASTM D624	26.5 kN/m min.
Hardness (°IRHD)	ASTM D1415	70 ± 5
Tensile retained	ASTM D412	70% min.
Ozone Resistance	ASTM D1149	No visible cracks
Water vapour transmission	AS/NZS 4858	1.35 g/m <sup>2</sup> /24 hours

### Toll Free Technical Services: 0800 227 339 (New Zealand)

The technical details, recommendations and other information contained in this data sheet are given in good faith and represent the best of our knowledge and experience at the time of printing. It is your responsibility to ensure that our products are used and handled correctly and in accordance with any applicable New Zealand & Australian Standards, our instructions and recommendations and only for the uses they are intended. We also reserve the right to update information without prior notice to you to reflect our ongoing research and development program. Country specific recommendations, depending on local standards, codes of practice, building regulations or industry guidelines, may effect specific installation recommendations. The supply of our products and services is also subject to certain terms, warranties and exclusions, which may have already been disclosed to you in prior dealings or are otherwise available to you on request. You should make yourself familiar with them.

© ARDEX New Zealand Ltd 2021.

All aforementioned products are the trademarks of ARDEX New Zealand Ltd, its licensors and affiliates. This data sheet was issued in August 2021. Always refer to [ardex.co.nz](http://ardex.co.nz) for the latest technical data from ARDEX New Zealand Ltd.